



**FIRE
TECHNOLOGY
SERVICES**

Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Fax: +44 (0)113 278 0306
Web: <http://www.bttg.co.uk>
Email: CSLeeds@bttg.co.uk

Our Ref: 27/01475B/10/08
Your Ref:
Order No:

13 November 2008
Page 1 of 3

Client: XL Screen
Route de Jalerieu
Les Avenieres
38630
France

Job Title: **Fire Test on One Sample of Fabric**

Material Received: 23 October 2008

Description of Sample: One sample of fabric, referenced: **Screen Vision 3% (SV 3%)**.

Brief: Fire Technology Services were requested to carry out a fire test on the sample supplied to BS 5867 Part 2.

UKAS Accreditation: Our Laboratories are UKAS accredited. However, it should be noted that tests marked * are not UKAS accredited in this report. They are not included in the UKAS Accreditation Schedule for our laboratory, either due to the work not conforming fully to the standard (e.g. reduced number of specimens) or to it being outside the scope of our accreditation, or subcontracted.

Uncertainty: An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.





Fire Tests According to BS 5867-2:Type B:2008

Fabrics for curtains, drapes and window blinds – Flammability requirements, Specification

Date of Test: 12/11/08

Procedure

The specimen were tested in accordance with BS EN ISO 15025:Procedure A:2002, as required by BS 5867:Type B.

The specimens were tested as received using a flame application time of 15 seconds.

Requirements

BS 5867 states that:-

‘No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of the sample. If any part of any hole or any part of any flame, reaches the top edge or either vertical edge, or if there is any separation of any flaming debris droplets in the testing of one specimen, a further six specimens shall be tested. If all six new specimens comply with the above requirements, the fabric shall be deemed to conform to the requirements for type ‘B’ of this British Standard.’

Results

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Number of specimens where the hole reached any edge	–	0
Number of specimens where the flame reached any edge	–	0
Number of specimens where there was flaming debris droplets	–	0

Comments

The results indicate the sample meets the Type B performance requirements.



**FIRE
TECHNOLOGY
SERVICES**

Date: 13 November 2008
Our Ref: 27/01475B/10/08
Your Ref:
Order No:
Page 3 of 3

XL Screen

The information contained on page no's 1/3 of this certificate is hereby certified to be a correct statement of the tests and investigations carried out by the FTS on the materials referred to.

Signed *B. Marsden* Date *13/11/08*
Mrs. B. Marsden
Fire Technician

Reported By *P. Doherty* Date *13/11/08*
Mr P Doherty
Operational Head